

bpi brentwood plastics, inc.

8734 SUBURBAN TRACKS • ST. LOUIS • MISSOURI • 63144

Phone 314) 968-1135 • www.brentwoodplastics.com • Fax 314) 968-4276

G P C

General Purpose Clear (GPC) is a medium duty film with good sealability. Used for a variety of applications, clarity is adequate for most retail applications. Only available in high slip. FDA and Kosher approved.

<u>Properties</u>	<u>test method</u>	<u>typical value*</u>	<u>unit</u>
Haze	ASTM D 1003	6.5	%
Gloss 45 °	ASTM D 2457	70	-
1% secant modulus MD TD	ASTM D 882	25,300 28,000	psi
Dart Impact F50	ASTM D1709A	75	gm.
Elmendorf tear MD TD	ASTM D 1922	320 340	gm.
Tensile Break Strength MD TD	ASTM D 882	3,400 2,800	psi
Tensile Elongation @ break MD TD		290 510	% %
Tensile Yield MD TD		1,400 1,330	psi psi
Elongation @ yield MD TD		13.4 12.2	% %

* data obtained on 2.0 mil film is typical and not to be construed as specification limits. Establishing suitability for any end use is the end user's responsibility. No warranties are expressed or implied.