

bpi brentwood plastics, inc.

8734 SUBURBAN TRACKS • ST. LOUIS • MISSOURI • 63144

Phone 314) 968-1135 • www.brentwoodplastics.com • Fax 314) 968-4276

SHRINK

SHRINK is an industrial shrink bundling film made for packaging bottles, canned goods, bagged pet food and corrugated boxes. Unless otherwise specified, targeted MD shrink is 68% and TD is 3% to ensure a tight “bull’s eye” closure on the package side. Low slip means cases can be stacked without sliding.

| <u>Properties</u> | <u>test method</u> | <u>typical value*</u> | <u>unit</u> |
|-------------------------------|--------------------|-----------------------|-------------|
| Haze | ASTM D 1003 | 19 | % |
| Gloss 45 ° | ASTM D 2457 | 46 | - |
| 1% secant modulus MD | ASTM D 882 | 27,200 | psi |
| TD | | 32,300 | |
| Dart Impact F50 | ASTM D1709A | 260 | gm. |
| Elmendorf tear MD | ASTM D 1922 | 450 | gm. |
| TD | | 610 | |
| Tensile Break Strength MD | ASTM D 882 | 4,100 | psi |
| TD | | 3,950 | |
| Tensile Elongation @ break MD | | 520 | % |
| TD | | 630 | % |
| Tensile Yield MD | | 1,580 | psi |
| TD | | 1,470 | |
| Elongation @ yield MD | | 19.6 | % |
| TD | | 13.1 | % |

* data obtained on 2.0 mil film is typical and not to be construed as specification limits. Establishing suitability for any end use is the end user’s responsibility. No warranties are expressed or implied.