



brentwood plastics, inc.

8734 Suburban Tracks
St. Louis, MO 63144

Phone: 314.968.1135
Fax: 314.968.4276

www.brentwoodplastics.com

LLD Blend

LLD blend is a general purpose economy film comprised of butene LLD and conventional LDPE. COF is made to order. FDA compliant and Kosher approved. 100% recyclable

Successfully used for whole produce and as a sealant layer for laminations.

Typical Properties *

<u>Property</u>	<u>Test Method</u>	<u>Typical Value</u>	<u>Unit</u>
Gloss 45°	ASTM D 2457	54	
Haze	ASTM D 1003	14	%
Secant Modulus 1%	ASTM D 882	32,000 MD 33,700 TD	psi
Tensile Elongation Break	ASTM D 882	190 MD 80 TD	%
Elmendorf Tear	ASTM D 1922	908 MD 820 TD	gm
Dart Impact F 50	ASTM 1709 A	105	gm

\

* good faith estimates based on repeated testing of 1.3 mil film
Not to be construed as specification limits
It is the users responsibility to determine suitability for any application, no warranties are expressed or implied.